FerroSoft Print ASLAN FF 480

Item number: ASL U1400801440

Printable, especially flexible ferrous film for placing magnets

This film containing iron turns every smooth substrate into a magnetically-receptive surface. Thanks to the special softness of the film it can be ideally printed with solvent, eco-solvent and UV printing systems as well as the latex printing system HP 500 and in screen printing, and lends itself perfectly to creative customisation.

It can be cut to any imaginable shape or size, is easy to apply and can be combined with other self-adhesive films. In combination with ASLAN's transparent blackboard and whiteboard films for instance, printed graphics can also be written on with chalk or whiteboard markers.

Construction

Face film: Polyethylene based ferrous film with PVC laminate (white, matt)

Thickness: ~ 480 µm (~ 18.9 mil)

Adhesive: Polyacrylic pressure sensitive adhesive Square quantity: ~ 55 g/m²

Release liner: double sided PE coated paper Square weight: ~ 140 g/m²

Characteristics

Adhesive strength (ASTM D903): Immediately: ~ 11.5 N/25 mm

After 72 hours: ~ 18 N/25 mm

Dimensional stability: Applied onto aluminium No shrinkage measurable

after 48 hours stored at 70° C (158 °F) (25 x 25 cm)

Chemical resistance: In a preece test of 24 hours, the applied film is resistant to most petroleum-based oils,

greases and aliphatic solvents, mild acids and mild alkalis.

Temperature: Application temperature: min 15 °C (59 °F)

Service temperature range: -30 °C (-22 °F) up to +80 °C (176 °F)



Official Distributor for



To place an order or for more info, contact your local sales rep:

Northern CA Doug King 408.701.7202

Central/SouthernCA/Hawaii Sommer Della Bitta 916.947.2602

Southern CA Dereck Cruz 626.201.8932 Washington/Oregon

Chuck Vandervort 206.235.4191 Pam Pare 503.317.6759 **Destinee Vaughn** 503.713.1368



FerroSoft Print ASLAN FF 480

Item number: ASL U1400801440

Processing

Application:

In general the film can be applied dry. The substrate must be free of dust, grease and oil and should not be porous.

If the substrate is smooth, it can be applied wet, but the water must be squeegeed out very well to avoid the formation of bubbles later.

Ferrous films are developed for indoor applications only. Due to the variety of varnishes and different substrates of indoor walls, it is highly recommended to perform adhesion tests prior to the application, even if the film is equipped with a strong adhesive. To play safe, it is recommended to sand varnished and porous walls and to treat those with a primer.

Further application tips for ferrous films are available for download in the user area of the ASLAN website.

Printability:

The material is printable with solvent, eco-solvent, UV curable as well as screen printing inks. It is also suited for the latex printing system HP 500. In case of insufficient drying of the printing inks, the film will be sodded and the adhesive negatively affected.

Processing instruction:

To avoid tunneling, we recommend to store rolls tightly wrapped on a 3" core and tape them up. This is also valid for combinations with most other self-adhesive films. Self-testing is highly recommended to avoid tunneling.

Storage life:

Before application the films can be stored up to 2 years from date of production. The film must be stored at room temperature (15-25 °C / 59-77 °F) and at a relative air humidity of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either standing vertically or in a purposely designed `hanging' racks.

State 06|2022

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our **latest** knowledge.





To place an order or for more info, contact your local sales rep:

Northern CA
Doug King
408.701.7202
Central/SouthernCA/Hawaii
Sommer Della Bitta
916.947.2602
Southern CA
Dereck Cruz
626.201.8932

Washington / Oregon
Chuck Vandervort
206.235.4191
Pam Pare
503.317.6759
Destinee Vaughn
503.713.1368